

研究论文

用原位红外技术研究Ag-MoO<sub>3</sub>/ZrO<sub>2</sub>催化丙烯气相环氧化反应

金国杰<sup>1,2</sup>, 郭杨龙<sup>1</sup>, 刘晓晖<sup>1</sup>, 姚伟<sup>1</sup>, 郭耘<sup>1</sup>, 卢冠忠<sup>\*,1</sup>

(<sup>1</sup>结构可控先进功能材料及其制备教育部重点实验室 华东理工大学工业催化研究所 上海 200237)

(<sup>2</sup>中国石化上海石油化工研究院 上海 201208)

收稿日期 2006-3-13 修回日期 2006-5-11 网络版发布日期 2006-10-25 接受日期 2006-7-7

摘要 制备了对丙烯直接气相环氧化具有优良催化性能的Ag-MoO<sub>3</sub>/ZrO<sub>2</sub>催化剂, 采用原位FT-IR技术研究了丙烯、环氧丙烷及丙烯和氧气混合气在载体和催化剂上的吸附及反应行为。研究表明, 丙烯在ZrO<sub>2</sub>载体和20%Ag-4%MoO<sub>3</sub>/ZrO<sub>2</sub>催化剂上吸附后, 均不发生化学反应, 而环氧丙烷在ZrO<sub>2</sub>载体上吸附后于400 °C发生开环反应, 在20%Ag-4%MoO<sub>3</sub>/ZrO<sub>2</sub>催化剂上吸附后于300 °C发生开环反应。当丙烯和氧气混合气在ZrO<sub>2</sub>载体上共吸附后, 随着反应温度从室温升高至400 °C, 二者开始反应生成CO<sub>2</sub>和H<sub>2</sub>O; 混合气在20%Ag-4%MoO<sub>3</sub>/ZrO<sub>2</sub>催化剂上共吸附后于350 °C开始反应。对比非负载型Ag-MoO<sub>3</sub>催化剂的研究结果可见, ZrO<sub>2</sub>载体的存在使催化剂的活性下降的同时, 提高了对产物环氧丙烷的选择性。

关键词 丙烯 气相环氧化 环氧丙烷 Ag-MoO<sub>3</sub>/ZrO<sub>2</sub>催化剂 原位红外光谱

分类号

## Study on the Direct Gas Phase Epoxidation of Propylene over Ag-MoO<sub>3</sub>/ZrO<sub>2</sub> Catalyst by *in situ* FT-IR

JIN Guo-Jie<sup>1,2</sup>, GUO Yang-Long<sup>1</sup>, LIU Xiao-Hui<sup>1</sup>, YAO Wei<sup>1</sup>, GUO Yun<sup>1</sup>, LU Guan-Zhong<sup>\*,1</sup>

(<sup>1</sup> Laboratory for Advanced Materials, Research Institute of Industrial Catalysis, East China University of Science and Technology, Shanghai 200237)

(<sup>2</sup> Shanghai Research Institute of Petrochemical Technology, China Petroleum and Chemical Corporation, Shanghai 201208)

**Abstract** The Ag-MoO<sub>3</sub>/ZrO<sub>2</sub> catalyst for the direct gas phase epoxidation of propylene was prepared. The *in situ* FT-IR technology was employed to study the adsorption and reaction behavior of propylene, propylene oxide (PO) and the mixture gas of propylene and oxygen on the surface of ZrO<sub>2</sub> support and Ag-MoO<sub>3</sub>/ZrO<sub>2</sub> catalyst. The studies show that propylene adsorbed on ZrO<sub>2</sub> support or 20%Ag-4%MoO<sub>3</sub>/ZrO<sub>2</sub> catalyst is stable. When the reaction temperature is more than 400 °C, the ring-opening reaction of propylene oxide adsorbed on ZrO<sub>2</sub> support happens; over the 20%Ag-4%MoO<sub>3</sub>/ZrO<sub>2</sub> catalyst, the ring-opening reaction of adsorbed propylene oxide occurs at 300 °C. As the reaction temperature rises to 400 °C, propylene adsorbed reacts with oxygen adsorbed on ZrO<sub>2</sub> support to form water and CO<sub>2</sub>; over the 20%Ag-4%MoO<sub>3</sub>/ZrO<sub>2</sub> catalyst, this surface reaction just takes place at 350 °C. Comparing with the unsupported Ag-MoO<sub>3</sub> catalyst, the presence of ZrO<sub>2</sub> support can increase the selectivity of PO and while decrease the conversion of propylene.

**Key words** [propylene](#) [gas phase epoxidation](#) [propylene oxide](#) [Ag-MoO<sub>3</sub>/ZrO<sub>2</sub> catalyst](#) [in situ FT-IR](#)

DOI:

通讯作者 卢冠忠 [gzhlu@ecust.edu.cn](mailto:gzhlu@ecust.edu.cn)

扩展功能

### 本文信息

► [Supporting info](#)

► [PDF\(320KB\)](#)

► [\[HTML全文\]\(0KB\)](#)

► [参考文献](#)

### 服务与反馈

► [把本文推荐给朋友](#)

► [加入我的书架](#)

► [加入引用管理器](#)

► [复制索引](#)

► [Email Alert](#)

► [文章反馈](#)

► [浏览反馈信息](#)

### 相关信息

► [本刊中包含“丙烯”的相关文章](#)

► [本文作者相关文章](#)

· [金国杰](#)

· [郭杨龙](#)

· [刘晓晖](#)

· [姚伟](#)

· [郭耘](#)

· [卢冠忠](#)

·