

新型氰基桥联二维配位聚合物 $\{[\text{Fe}(\text{salen})]_2[\text{Ni}(\text{CN})_4]\}_n$ 的合成、晶体结构和磁性质

袁爱华,沈小平,郁开北,陆路德,周伟,钟娟娟

华东船舶工业学院材料科学与工程学院;江苏大学化学化工学院;中国科学院 成都有机化学研究所

南京理工大学材料化学实验室

收稿日期 修回日期 网络版发布日期 接受日期

摘要 将 $[\text{Fe}(\text{salen})\text{NO}_3]$ 的甲醇溶液和 $\text{K}_2[\text{Ni}(\text{CN})_4] \cdot \text{H}_2\text{O}$ 水溶液通过 H 管扩散反应,得到了一个新型氰基桥联配位聚合物 $\{[\text{Fe}(\text{salen})]_2[\text{Ni}(\text{CN})_4]\}_n$ (H_2salen 为 N, N'-二水杨醛缩乙二胺席夫碱)。该化合物属四方晶系。空间群 $P4/ncc$, 晶胞参数为 $a=b=1.4216(2)\text{nm}$, $c=1.7471(5)\text{nm}$, $V=3.5308(12)\text{nm}^3$, $Z=4$ 。该配合物通过 Ni-CN-Fe(salen)-NC-Ni 链连接形成二维枕形网格结构, 其中键长 Ni-C $0.1876(3)\text{nm}$, Fe-N $0.2170(3)\text{nm}$, 键角 Fe-N-C $164.9(3)^\circ$, Ni-C-N $178.9(4)^\circ$; 金属中心 Ni(II) 和 Fe(III) 分别具有正方形和畸变八面体配位构型。变温磁化率研究表明, 配合物存在分子内反铁磁相互作用, 其 Fe(III) ... Fe(III) 交换积分为 -0.041cm^{-1} 。

关键词 [镍络合物](#) [铁络合物](#) [晶体结构](#) [磁性](#) [氰基](#) [席夫碱](#)

分类号 [0611.662](#)

Synthesis, Crystal Structure and Magnetic Properties of a Cyano-bridged Two-dimensional Coordination Polymer $\{[\text{Fe}(\text{salen})]_2[\text{Ni}(\text{CN})_4]\}_n$

Yuan Aihua, Shen Xiaoping, Yu Kaibei, Lu Lude, Zhou Wei, Zhong Juanjuan

School of Material Science and Technology, East China Shipbuilding Institute; School of Chemistry and Chemical Engineering, Jiangsu University; Analysis Center, Chengdu Branch of Chinese Academy of Sciences; Material Chemistry Laboratory, Nanjing University of Science and Technology

Abstract A cyano-bridged coordination polymer, $\{[\text{Fe}(\text{salen})]_2[\text{Ni}(\text{CN})_4]\}_n$ ($\text{salen} = \text{N}, \text{N}'\text{-ethylenebis}(\text{salicylideneimino})\text{-dianion}$), prepared by slow diffusion of an aqueous solution of $\text{K}_2[\text{Ni}(\text{CN})_4] \cdot \text{H}_2\text{O}$ and a MeOH solution of $[\text{Fe}(\text{salen})\text{NO}_3]$ in an H tube, has been characterized by X-ray structure analysis, IR spectra and magnetic measurements. The complex crystallizes in the tetragonal space group $P4/ncc$ with $a = b = 1.4216(2)\text{ nm}$, $c = 1.7471(5)\text{ nm}$, $V = 3.5308(12)\text{ nm}^3$, $Z = 4$. The product assumes a two-dimensional network structure consisting of pillow-like octanuclear $[-\text{Ni}-\text{CN}-\text{Fe}(\text{salen})-\text{NC}-]_4$ units with dimensions: Ni-C = $0.1876(3)\text{ nm}$, Fe-N = $0.2170(3)\text{ nm}$, Fe-N-C = $164.9(3)^\circ$, Ni-C-N = $178.9(4)^\circ$. The two metal atoms Ni(II) and Fe(III) have square and slightly distorted octahedral arrangements, respectively. The variable temperature magnetic susceptibility, measured in the $5 \sim 300\text{ K}$ range, indicates the presence of a weak intralayer antiferromagnetic interaction and gives an Fe(III) ... Fe(III) exchange integral of -0.041 cm^{-1} .

Key words [NICKEL COMPLEX](#) [IRON COMPLEX](#) [CRYSTAL STRUCTURE](#) [MAGNETISM](#) [CYANO GROUP](#) [SCHIFF BASE](#)

DOI:

通讯作者

扩展功能

本文信息

▶ [Supporting info](#)

▶ [PDF\(0KB\)](#)

▶ [HTML全文\(0KB\)](#)

▶ [参考文献](#)

服务与反馈

▶ [把本文推荐给朋友](#)

▶ [加入我的书架](#)

▶ [加入引用管理器](#)

▶ [复制索引](#)

▶ [Email Alert](#)

▶ [文章反馈](#)

▶ [浏览反馈信息](#)

相关信息

▶ [本刊中包含“镍络合物”的相关文章](#)

▶ 本文作者相关文章

· [袁爱华](#)

· [沈小平](#)

· [郁开北](#) [陆路德](#)

· [周伟](#)

· [钟娟娟](#)