

研究简报

热解乙氧基铝制备次级电子发射膜

谢伯兴

昆明物理研究所 昆明

收稿日期 1987-9-1 修回日期 1989-5-23 网络版发布日期 2009-12-16 接受日期

摘要

利用某些有机烷氧基金属化合物的热分解,可在玻璃、金属、陶瓷或半导体基片上沉积相应的金属氧化物次级发射膜。例如:由乙氧基镁(或铝)的热解制得MgO(或Al₂O₃)膜。本工作由自制乙氧基铝和五氯化钼,在玻璃基底上热解沉积制得合适电阻率的次级发射膜Al₂O₃:Mo。膜厚1000Å,电阻率10⁷-10⁸Ω·cm,最大次级电子发射系数 $\delta_{max}=3.1$,热解条件为450℃,12min。

关键词 次级电子发射膜 热解沉积 乙氧基铝

分类号

FABRICATION OF SECONDARY EMISSION FILM BY PYROLYZATION OF ALUMINIUM ETHOXIDE

Xie Baixing

Kunming Institute of Physics, Kunming

Abstract

A metal-oxide secondary emission film can be deposited on glass, ceramic or semiconductor substrates by thermal decomposition of an organo-metal alkoxide. For instance, MgO (or Al₂O₃) secondary emission film can be obtained from magnesium (or Aluminium) ethoxide thermal decomposition. In the present method, Al₂O₃: Mo secondary emission film has been made from thermal decomposition of home-made Aluminium ethoxide and Molybdenum pentachloride. The depositing conditions are T = 450℃ and t=12min for the about 1000Å thickness of film to get. The maximum secondary emission coefficient and resistivity of the film are $\delta_{max}=3.1$, $\rho=10^7-10^9$, Ω·cm respectively.

Key words [Secondary emission film](#) [Pyrolytic deposition](#) [Aluminium ethoxide](#)

DOI:

通讯作者

作者个人主页 谢伯兴

扩展功能

本文信息

▶ [Supporting info](#)

▶ [PDF\(702KB\)](#)

▶ [\[HTML全文\]\(OKB\)](#)

▶ [参考文献\[PDF\]](#)

▶ [参考文献](#)

服务与反馈

▶ [把本文推荐给朋友](#)

▶ [加入我的书架](#)

▶ [加入引用管理器](#)

▶ [复制索引](#)

▶ [Email Alert](#)

▶ [文章反馈](#)

▶ [浏览反馈信息](#)

相关信息

▶ [本刊中包含“次级电子发射膜”的相关文章](#)

▶ 本文作者相关文章

· [谢伯兴](#)