

炭气凝胶孔结构对其负载的 TiO_2 光催化降解甲基橙性能的影响

崔华楠, 赵振华, 梁业如, 石建英, 吴丁财, 刘鸿, 符若文

中山大学化学与化学工程学院, 广东广州 510275

CUI Huanan, ZHAO Zhenhua, LI ANG Yeru, SHI Jianying*, WU Dingcai*, LIU Hong, FU Ruowen

School of Chemistry and Chemical Engineering, Sun Yat-sen University, Guangzhou 510275, Guangdong, China

- 摘要
- 参考文献
- 相关文章

Download: PDF (428KB) [HTML \(1KB\)](#) Export: BibTeX or EndNote (RIS) Supporting Info

摘要 选用两种孔径不同的炭气凝胶 CA125 和 CA500 制备了碳含量为 20% 的 TiO_2/CA 光催化剂, 采用 X 射线衍射、扫描电镜和 N₂ 吸附-脱附对催化剂进行了表征, 并考察了其光催化降解甲基橙反应性能。结果表明, TiO_2/CA 样品中 TiO_2 主要以锐钛矿相存在, 伴随有少量的金红石相, 且均匀分散于炭气凝胶的表面。催化剂的孔隙率分析表明, 孔结构直接影响到催化剂的光催化活性, 以中孔为主的 $TiO_2/CA125$ 活性要远高于 $TiO_2/CA500$ 。这主要源于中孔良好的吸附性能及其合适的空间限域效应。

关键词: 炭气凝胶 氧化钛 限域效应 光催化 甲基橙 降解

Abstract: Two kinds of carbon aerogel (CA), CA125 and CA500, with pore diameters of ~18 nm and > 50 nm, respectively, were used as supports to prepare TiO_2/CA photocatalysts with the CA content of 20%. X-ray diffraction, scanning electron microscopy and N₂ adsorption-desorption were used to characterize the crystal structure, morphology, and pore structures of the TiO_2/CA photocatalysts, respectively. The loaded TiO_2 was mainly anatase with a little amount of rutile, which was homogeneously dispersed on the CA support. The activity of $TiO_2/CA125$ was much higher than that of $TiO_2/CA500$ in the photodegradation of methyl orange. The photodegradation rate over TiO_2/CA is mainly influenced by the pore structure of the catalysts. The favorable adsorption and suitable confinement effect of mesopore structure are beneficial to the photodegradation of methyl orange. Therefore, $TiO_2/CA125$ with the large amount of mesopores displays the higher photocatalytic activity than $TiO_2/CA500$.

Keywords: [carbon aerogel](#), [titania](#), [confinement effect](#), [photocatalysis](#), [methyl orange](#), [degradation](#)

收稿日期: 2010-09-30; 出版日期: 2010-12-03

Service

- ▶ 把本文推荐给朋友
- ▶ 加入我的书架
- ▶ 加入引用管理器
- ▶ Email Alert
- ▶ RSS

作者相关文章

引用本文:

.炭气凝胶孔结构对其负载的 TiO_2 光催化降解甲基橙性能的影响[J] 催化学报, 2011,V32(2): 321-324

.Influence of Carbon Aerogel (CA) Pore Structure on Photodegradation of Methyl Orange over TiO_2/CA [J], 2011,V32(2): 321-324

链接本文:

<http://www.chxb.cn/CN/10.3724/SP.J.1088.2011.00932> 或 <http://www.chxb.cn/CN/Y2011/V32/I2/321>

没有本文参考文献

- [1] 蔡陈灵, 王金果, 曹锋雷, 李和兴, 朱建*. 非水溶剂热法制备 (001) 面暴露的 F/ TiO_2 纳米晶及其光催化活性[J]. 催化学报, 2011,32(5): 862-871
- [2] 陈立静, 王婷, 陈锋*, 张金龙. 以酚醛树脂为碳源的碳改性 TiO_2 可见光光催化剂[J]. 催化学报, 2011,32(4): 699-703
- [3] 余长林^{1,*}, 杨凯¹, 舒庆¹, YU Jimmy C², 操芳芳¹, 李鑫¹. WO_3/ZnO 复合光催化剂的制备及其光催化性能[J]. 催化学报, 2011,32(4): 555-565
- [4] 向全军, 余家国. 暴露 {001} 面 TiO_2 纳米片分等级花状结构的制备及其光催化活性[J]. 催化学报, 2011,32(4): 525-531
- [5] 王后锦^{1,2}, 吴晓婧^{1,2}, 王亚玲^{1,2}, 焦自斌¹, 颜声威¹, 黄浪欢^{1,2}. 二氧化钛纳米管阵列光电催化同时降解苯酚和 Cr(VI)[J]. 催化学报, 2011,32(4): 637-642
- [6] 徐守斌, 江龙, 杨海刚, 宋远卿, 淡宜. 光诱导聚合制备聚噻吩/二氧化钛复合粒子的结构及光催化性能[J]. 催化学报, 2011,32(4): 536-545
- [7] 县涛^{1,2}, 杨华^{1,2}, 戴剑锋^{1,2}, 魏智强^{1,2}, 马金元², 冯旺军². 粒径可控的纳米铁酸铋的制备及其光催化性能[J]. 催化学报, 2011,32(4): 618-623
- [8] 赵崇斌, 杨杭生, 周环, 邱发敏, 张孝彬. TiO_2 纳米管阵列负载 MnO_x 复合催化剂的脱硝性能[J]. 催化学报, 2011,32(4): 666-671
- [9] 黄涛, 张国亮, 王玲, 刘良军, 孙茜萍. 以尿素为氮源制备氮改性二氧化钛及其改性机理[J]. 催化学报, 2011,32(3): 508-512
- [10] 李纲, 刘昉, 阳启华, 张昭. Si掺杂对 TiO_2 空心微球微结构和光催化性能的影响[J]. 催化学报, 2011,32(2): 286-292
- [11] 刘红旗, 顾晓娜, 陈锋, 张金龙. BIOCl 纳米片微球的制备及其形成机理[J]. 催化学报, 2011,32(1): 129-134
- [12] 温艳媛, 丁昆明. Ag@AgCl 修饰的锐钛矿相 TiO_2 纳米管的制备及其光催化性能[J]. 催化学报, 2011,32(1): 36-45
- [13] 王秀瑜, 张敬畅, 朱红. Pt-Au/CNT@ TiO_2 作为甲醇燃料电池的高活性阳极催化剂[J]. 催化学报, 2011,32(1): 74-79

- [14] 郑华荣, 崔言娟, 张金水, 丁正新, 王心晨. Pt 助剂对 N掺杂 TiO₂ 可见光光催化性能的影响[J]. 催化学报, 2011, 32(1): 100-105
- [15] 史慧贤 1, 张天永 1,2, 王红亮 3, 王晓 1, 何萌 1. 纳米 TiO₂ 光催化萘转化为 α-萘酚[J]. 催化学报, 2011, 32(1): 46-50