

Ag@AgCl 修饰的锐钛矿相 TiO_2 纳米管的制备及其光催化性能

温艳媛, 丁昆明

华东师范大学化学系, 上海 200062

WEN Yanyuan, DING Hanming*

Department of Chemistry, East China Normal University, Shanghai 200062, China

- 摘要
- 参考文献
- 相关文章

Download: PDF (796KB) [HTML \(1KB\)](#) Export: BibTeX or EndNote (RIS) Supporting Info

摘要 首先采用水热合成法和双氧水处理制备了具有锐钛矿相的 TiO_2 纳米管, 然后通过沉淀和光化学反应将 Ag@AgCl 纳米粒子负载于其上, 从而制得 TiO_2 纳米管负载的表面等离子体光催化剂。结果表明, 经 Ag@AgCl 纳米粒子修饰后, 锐钛矿相 TiO_2 纳米管因表面等离子共振效应而对可见光具有明显的响应, 光生电子-空穴对更容易分离, 因而 TiO_2 纳米管的可见光催化活性提高。该催化剂对亚甲基蓝分子具有很强的吸附能力, 可见光下照射 1 h 后即可完全降解脱色。另外, 该光催化剂重复使用 5 次后, 亚甲基蓝脱色率仍保持在 90% 以上。

关键词: 银 氯化银 二氧化钛 纳米管 表面等离子共振 可见光响应 光催化 亚甲基蓝

Abstract: The combination of TiO_2 nanotubes and a surface plasmon resonance (SPR) photocatalyst used their large adsorption capacity and wide visible light response, respectively, and a synergistic effect to enhance photocatalytic activity under visible light irradiation. Anatase TiO_2 nanotubes were prepared by hydrothermal synthesis, a hydrogen peroxide treatment, and calcination at 400 °C. AgCl nanoparticles were then loaded onto the TiO_2 nanotubes by a precipitation reaction, and some of the AgCl particles were reduced to Ag particles under halogen tungsten lamp irradiation. This gave a visible light SPR photocatalyst of Ag@AgCl/ TiO_2 nanotubes that exhibited high photocatalytic activity, which was due to its large adsorption capacity, wide visible light response due to the SPR effect, fast separation of photogenerated electron-hole pairs, and strong oxidizing ability of Cl^0 generated by combining Cl^- ions with photoexcited holes. Methylene blue dye was thoroughly decolorized within 1 h in the presence of this photocatalyst under visible light irradiation. In addition, the photocatalyst was stable after recycling the photocatalytic reaction five times.

Keywords: silver, silver chloride, titanium dioxide, nanotube, surface plasmon resonance, visible light activation, photocatalysis, methylene blue

收稿日期: 2010-07-13; 出版日期: 2010-11-01

Service

- ▶ 把本文推荐给朋友
- ▶ 加入我的书架
- ▶ 加入引用管理器
- ▶ Email Alert
- ▶ RSS

作者相关文章

引用本文:

.Ag@AgCl 修饰的锐钛矿相 TiO_2 纳米管的制备及其光催化性能[J] 催化学报, 2011,V32(1): 36-45.Preparation and Photocatalytic Activity of Ag@AgCl Modified Anatase TiO_2 Nanotubes[J], 2011,V32(1): 36-45

链接本文:

[http://www.chxb.cn/CN/10.1016/S1872-2067\(10\)60157-X](http://www.chxb.cn/CN/10.1016/S1872-2067(10)60157-X) 或 <http://www.chxb.cn/CN/Y2011/V32/I1/36>

没有本文参考文献

- [1] 蔡陈灵, 王金果, 曹锋雷, 李和兴, 朱建*.非水溶剂热法制备 (001) 面暴露的 F/TiO₂纳米晶及其光催化活性[J]. 催化学报, 2011,32(5): 862-871
- [2] 张丽, 刘福东a, 余运波, 刘永春, 张长斌, 贺泓b.CeO₂ 添加对 Ag/Al₂O₃ 催化剂低温氨氧化性能的影响[J]. 催化学报, 2011,32(5): 727-735
- [3] 陈立静, 王婷, 陈锋*, 张金龙, 以酚醛树脂为碳源的碳改性 TiO_2 可见光光催化剂[J]. 催化学报, 2011,32(4): 699-703
- [4] 王后锦1,2, 吴晓婧1,2, 王亚玲1,2, 焦自斌1, 颜声威1, 黄浪欢1,2.二氧化钛纳米管阵列光电催化同时降解苯酚和 Cr(VI)[J]. 催化学报, 2011,32(4): 637-642
- [5] 徐守斌, 江龙, 杨海刚, 宋远卿, 淡宜.光诱导聚合制备聚噻吩/二氧化钛复合粒子的结构及光催化性能[J]. 催化学报, 2011,32(4): 536-545
- [6] 县涛 1,2, 杨华 1,2, 戴剑锋 1,2, 魏智强 1,2, 马金元 2, 冯旺军 2.粒径可控的纳米铁酸铋的制备及其光催化性能[J]. 催化学报, 2011,32(4): 618-623
- [7] 赵崇斌, 杨杭生, 周环, 邱发敏, 张孝彬.TiO₂ 纳米管阵列负载MnO_x 复合催化剂的脱硝性能[J]. 催化学报, 2011,32(4): 666-671
- [8] 余长林1,* , 杨凯 1, 舒庆 1, YU Jimmy C2, 操芳芳 1, 李鑫 1.WO₃/ZnO 复合光催化剂的制备及其光催化性能[J]. 催化学报, 2011,32(4): 555-565
- [9] 向全军, 余家国.暴露 {001} 面 TiO_2 纳米片分等级花状结构的制备及其光催化活性[J]. 催化学报, 2011,32(4): 525-531
- [10] 黄涛, 张国亮, 王玲, 刘良军, 孙茜萍.以尿素为氮源制备氮改性二氧化钛及其改性机理[J]. 催化学报, 2011,32(3): 508-512

- [11] 潘珍燕 1, 华丽 1, 乔云香 1, 杨汉民 2, 赵秀阁 1, 冯博 1, 朱闻闻 1, 侯震山 1,* . 纳米磁性颗粒负载的银催化剂催化苯乙烯环氧化反应[J]. 催化学报, 2011, 32(3): 428-435
- [12] 吕永康 1, 郁瑞鑫 1, 任瑞鹏 1,2 . 在预吸附氧原子的 Ag(100) 面上氯乙烯环氧化反应的密度泛函理论研究[J]. 催化学报, 2011, 32(3): 451-455
- [13] 崔华楠, 赵振华, 梁业如, 石建英, 吴丁财, 刘鸿, 符若文 . 炭气凝胶孔结构对其负载的 TiO₂ 光催化降解甲基橙性能的影响[J]. 催化学报, 2011, 32(2): 321-324
- [14] 李纲, 刘昉, 阳启华, 张昭 . Si 掺杂对 TiO₂ 空心微球微结构和光催化性能的影响[J]. 催化学报, 2011, 32(2): 286-292
- [15] 刘红旗, 顾晓娜, 陈锋, 张金龙 . BIOCl 纳米片微球的制备及其形成机理[J]. 催化学报, 2011, 32(1): 129-134