

Ni / MH电池负极用高容量稀土-镁-镍基储氢合金 [\(PDF\)](#)

《西安交通大学学报》自然版[ISSN:0253-987X/CN:61-1069/T] 期数: 2008年第03期 页码: 377-380 栏目: 出版日期: 2008-03-10

Title: Structural and Electrochemical Properties of High Capacity MI-Mg-Ni Based Hydrogen Storage Alloys

文章编号: 0253-987X (2008) 03-0377-04

作者: 韩树民 1; 李媛 1; 张忠 2; 朱惜林 1; 李金滑2; 鬼琳 1

1. 燕山大学环境与化学工程学院, 066004, 秦皇岛; 2. 燕山大学亚稳材料制备技术与科学国家重点实验室, 066004, 秦皇岛

Author(s): HAN Shumin 1; LI Yuan 1; ZHANG Zhong 2; ZHU Xilin 1; LI Jinhua 2; HU Lin 1

1. School of Environmental and Chemical Engineering, Yanshan University, Qinhuangdao 066004, China; 2. State Key Laboratory of Metastable Materials Science and Technology, Yanshan University, Qinhuangdao 066004, China

关键词: Ni / MH电池; 储氢合金; 稀土-镁-镍基合金

Keywords: Ni / MH battery; hydrogen storage alloy; rare earth Mg-Ni based alloy

分类号: TM912.9

DOI: 0253-987X (2008) 03-0377-04

文献标识码: A

摘要: 通过感应熔炼方法制备了稀土-镁-镍基储氢合金 $MIO.88Mg0.12Ni3.0Mn0.10Co0.55Al0.10$ (MI 代表富镧混合稀土). 采用XRD和SEM分析了合金的微观结构, 发现该合金主要由 $CaCu5$ 型相、 $Ce2Ni7$ 型相和 $Pr5Co19$ 型相组成. 电化学测试结果表明: 合金的放电容量可以达到 $386 \text{ mA}\cdot\text{h/g}$, 比商品 $AB5$ 型合金($332 \text{ mA}\cdot\text{h/g}$)高出 16.3% ; 在 1100 mA/g 的放电电流密度下, 合金的高倍率放电性能可以达到 62% , 高于商品 $AB5$ 型合金(45%); 充放电循环 300 次后, 合金的放电容量降低到 $315 \text{ mA}\cdot\text{h/g}$, 为最大放电容量的 81.5% .

Abstract: The rare earth Mg-Ni based hydrogen storage alloy $MIO.88Mg0.12Ni3.0Mn0.10Co0.55Al0.10$ ($MI=La$ -rich mischmetal) was prepared by inductive melting. The micro structure was analyzed by XRD and SEM. The alloy consists primarily of $CaCu5$ type phase, $Ce2Ni7$ type phase and $Pr5Co19$ type phase. The electrochemical measurements show that the maximum discharge capacity reaches to $386 \text{ mA}\cdot\text{h/g}$, 16.3% higher than that of the commercial $AB5$ type alloy ($332 \text{ mA}\cdot\text{h/g}$). For the discharge current density of 1100 mA/g , the higher rate discharge ability gets 62% , while that of the commercial $AB5$ type alloy is only 45% . The discharge capacity decreases to $315 \text{ mA}\cdot\text{h/g}$ after 300 th cycle, 81.5% of the maximum discharge capacity.

参考文献/REFERENCES

- [1] PAN Hongge, MA Jianxin, WANG Chunsheng, et al. Studies on the electrochemical properties of $MINi4$ $32-x$ Co_x $Al0.7$ hydride alloy electrodes [J]. J Alloys Compd, 1999, 293 / 295: 648-652.
- [2] KADIR K, SAKAI T, UEHARA I. Structural investigation and hydrogen capacity of $LaMg_2Ni_9$ and $(Y_0.65Ca_0.35)(Mg_1.32Ca_0.68)Ni_9$ of the AB_2C_9 type structure [J]. J Alloys Compd, 2000, 302(1 / 2): 112-117.

导航/NAVIGATE

本期目录/Table of Contents

下一篇/Next Article

上一篇/Previous Article

工具/TOOLS

引用本文的文章/References

下载 PDF/Download PDF(746KB)

立即打印本文/Print Now

推荐给朋友/Recommend

查看/发表评论/Comments

统计/STATISTICS

摘要浏览/Viewed 215

全文下载/Downloads 164

评论/Comments



- [3] CHEN J, TAKESHITA H T, TANAKA H, et al. Hydriding properties of LaNi₃ and CaNi₃ and their substitutes with PuNi₃ structure [J]. J Alloys Compd, 2000, 302(1 / 2): 304 313.
- [4] KOHNO T, YOSHIDA H, KAWASHIMA F, et al. Hydrogen storage properties of new ternary system alloys: La₂MgNi₉, La₅Mg₂Ni₂₃, La₃MgNi₁₄ [J]. J Alloys Compd, 2000, 311(2): L5 L7.
- [5] AKIBA E, HAYAKAWA H, KOHNO T. Crystal structure of novel La Mg Ni hydrogen absorbing alloys [J]. J Alloys Compd, 2006, 408 / 412: 280 283.
- [6] PAN Hongge, LIU Yongfeng, GAO Mingxia, et al. The structural and electrochemical properties of La_{0.7}Mg_{0.3}(Ni_{0.85}Co_{0.15})_x (x = 0~5) hydrogen storage alloys [J]. Int J Hydrogen Energy, 2003, 28(11): 1219 1228.
- [7] LIU Yongfeng, PAN Hongge, GAO Mingxia, et al. Influences of Ni addition on the structures and electrochemical properties of La_{0.7}Mg_{0.3}Ni_{2.65+x}Co_{0.75}Mn_{0.1} (x = 0~0.5) hydrogen storage alloys [J]. J Alloys Compd, 2005, 389(1 / 2): 281 289.
- [8] LIAO B, LEI Y Q, CHEN L X, et al. Effect of Co substitution for Ni on the structural and electrochemical properties of La₂Mg(Ni_{1-x}Co_x)₉ (x = 0~1~0.5) hydrogen storage electrode alloys [J]. Electrochim Acta, 2004, 50(4): 1057 1063.
- [9] LIU Yongfeng, PAN Hongge, ZHU Yunfeng, et al. Influence of Mn content on the structural and electrochemical properties of the La_{0.7}Mg_{0.3}Ni_{4.25-x}Co_{0.75}Mn_x hydrogen storage alloys [J]. Mater Sci Eng: A, 2004, 372(1 / 2): 163 172.
- [10] LIAO B, LEI Y Q, CHEN L X, et al. The effect of Al substitution for Ni on the structure and electrochemical properties of AB₃ type La₂Mg(Ni_{1-x}Al_x)₉ (x = 0~0.05) alloys [J]. J Alloys Compd, 2005, 404 / 406: 665 668.
- [11] LI M, HAN S M, LI Y, et al. Study on the phase structure and electrochemical properties of RE_{0.93}Mg_{0.07}Ni_{2.96}Co_{0.60}Mn_{0.37}Al_{0.17} hydrogen storage alloy [J]. Electrochim Acta, 2006, 51(26): 5926 5931.
- [12] ZHANG Zhong, HAN Shumin, LI Yuan, et al. Electrochemical properties of Mn_{1-x}Mg_xNi_{3.0}Mn_{0.10}Co_{0.55}Al_{0.10} (x = 0~0.05~0.30) hydrogen storage alloys [J]. J Alloys Compd, 2007, 431(1 / 2): 208 211.
- [13] 张羊换, 董小平, 王国清, 等. 铸态及快淬态La₂Mg(Ni_{0.85}Co_{0.15})₉Cr_x (x = 0~0.2) 电极合金的微观结构及电化学性能 [J]. 稀有金属材料与工程, 2006, 35(6): 876 879.
ZHANG Yanghuan, DONG Xiaoping, WANG Guoqing, et al. Microstructures and electrochemical performances of La₂Mg(Ni_{0.85}Co_{0.15})₉Cr_x (x = 0~0.2) electrode alloys prepared by casting and rapid quenching [J]. Raremetal Materials and Engineering, 2006, 35(6): 876 879.
- [14] IWAKURA C, OURAY T, INOUE H, et al. Effects of substitution with foreign metals on the crystallographic, thermodynamic and electrochemical properties of AB₅ type hydrogen storage alloys [J]. Electrochim Acta, 1996, 41(1): 117 121

备注/Memo: -

更新日期/Last Update: